

The Sidings Business Park, SKIPTON, North Yorkshire, BD23 1TB Phone or Fax 01756 792525



Office: 30 Alexandra Crescent, ILKLEY, West Yorkshire, LS29 9ER, Phone or Fax 01943 603459 Reg. No. 3168606, VAT No. 659 9604 77

TEST CERTIFICATE

No. F161027/4

Testing to EN ISO 12952: 2010, Textiles - Assessment of the ignitability of Bedding Items

SAMPLE INFORMATION

Client MIP (UK) Ltd, Unit 9, Chartmoor Road, Chartwell Business Park, Leighton

Buzzard, Bedfordshire LU7 4WG

Sample Reference FBL/24/2/PI Date Received 07/12/16

Pre-treatment 5 cycles according to BS EN ISO 6330, procedure 9N.

Conditioning To at least the minimum requirements of EN ISO 12952 : 2010, Clause 9

TESTING

Following the pre-treatment above, the sample was conditioned and tested according to EN ISO 12952: 2010, Parts 1 & 2, Textiles - Assessment of the ignitability of Bedding Items using Ignition Sources 0 and 1 applied to the sample laid flat over a mineral wool fibre pad.

The following results relate only to the ignitability of the test specimen under the particular conditions of test. They are not intended as a means of assessing the full potential fire hazard of the bedding items in use.

RESULTS

	time to extinction		Result	
Specimen No	1	2	1	2
Smouldering Cigarette on top surface (min)	19	20	Non-ignition	Non-ignition
Smouldering Cigarette beneath top surface (min)	23	23	Non-ignition	Non-ignition
Small Open flame from above (sec)	0	0	Non-ignition	Non-iignition

CONCLUSION

The specimens tested showed Non-ignition when tested to EN ISO 12952 : 2010, Textiles - Assessment of the ignitability of Bedding Items, Part 1, and Ignition when tested to EN ISO 12952 : 2010, Textiles -

Mr J Firth

711

Technical Manager END OF REPORT